

663 RAPID REPAIR PASTE

100% Solids Epoxy Rapid Repair Paste

DESCRIPTION

663 Rapid Repair Paste is a multi-purpose 100% solids epoxy repair paste for fast-track repairs and an excellent adhesive for flooring accessory installations. 663 Rapid Repair Paste is a two-component thixotropic compound that is easily applied directly from the Dual Cartridge Kit, or using a putty knife, trowel or plastic applicator out of bulk kits.

USES

663 Rapid Repair Paste's easy workability and rapid cure time make it an ideal product for last minute "touch ups" to missed pop-outs or small cracks in a substrate prior to applying a coating system. 663 Rapid Repair Paste is used to repair chips, defects, small voids or "honeycombing" in horizontal, vertical and overhead concrete substrates. 663 Rapid Repair Paste's excellent bond strength, thick consistency and quick setting attributes make it an ideal adhesive to use when setting pre-formed "speed cove", terrazzo strips or termination caps. 663 Rapid Repair Paste can be sanded immediately after cure and is strong enough to be drilled, tapped or shaped as needed to conform to the substrate being repaired.

COVERAGE

663 Rapid Repair Paste can be applied to a "feather edge" as thinly as a blade can strike it off and to nearly infinite depth. Ideally, 663 Rapid Repair Paste is applied in lifts less than 3/8" and not over areas more than 2 times wider than the repair depth. Deeper fill repairs may require two or more lifts allowing for cure in between applications.

FEATURES

- VOC compliant
- Non-shrink
- Good working time, but fast cure time
- Easy 1:1 mix ratio
- Easy application
- High bond strength and tensile strength

TYPICAL PROPERTIES

Volume Mix Ratio	1:1
Viscosity (Mixed)	125,000 CPS
Solids Content (%)	100% solids
VOC	VOC/HAPs compliant
Application Temps	50° - 80° F
Hardness (ASTM D-2240)	85 (Shore D)
Gel Time	15 minutes
Dry to Touch (recoat with compatible product)	30 minutes
Through Cure (able to stand)	45 minutes

LIMITATIONS FOR BEST RESULTS:

- Do not thin this product.
- Do not apply when humidity exceeds 70% indoors.
- Allow each coat to dry to 'tack-free' prior to re-coat.
- When re-coating, always apply the next coat within 24 hours of completing the previous coat.
- Relatively thin applications ($\frac{1}{4}$ " width or depth) of 663 Rapid Repair Paste are best – avoid deep fill repairs in a single lift as minor cracking during cure may result.
- Mix thoroughly until a uniform gray color is achieved
- Tube Set applicator works best when material is above 65F.

PRODUCT APPLICATION

Apply by putty knife, trowel or plastic applicator. Tri-Chem product test data is based on environmental temperatures of 75^o F (24^o C). Viscosity and working time are always affected by temperatures above or below that mark. When applying product – always consider the ambient, surface, and product temperature at the time and place of installation.

COLOR

663 Rapid Repair Paste is only available in gray. The resin component is black and the hardener is white so when mixed properly a uniform gray color is achieved.

PRODUCT STORAGE

DO NOT allow Tri-Chem products to freeze. All Tri-Chem products should be properly stored above the floor on pallets or shelves, and in an area that has a constant minimum temperature of 50^o F (10^o C).

SURFACE PREPARATION

Always apply Tri-Chem products to a clean / sound substrate that is free of laitance, grease, oils, debris, and curing compounds. Concrete substrates should be cured for a minimum of 28 days prior to application of product [except as otherwise noted on the individual Product Data Sheet]. Whenever possible, remove existing coatings and/or flooring systems completely; if complete removal is not possible always perform tests to determine adhesion and compatibility to the existing flooring. Mechanical surface preparation to a CSP-2 minimum profile by means of a diamond grinding machine is the best and recommended preparation method for 663 Rapid Repair Paste. If the substrate is not properly prepared and the appropriate profile is not achieved, failure of the product to adhere to the substrate may occur.

CHEMICAL RESISTANCE

Always refer to Tri-Chem's chemical resistant chart for specific information on each product / system or contact Tri-Chem directly.

CLEAN UP

Application tools and equipment can be cleaned with soap and water immediately after use or with solvent once the product has begun to cure.

DISPOSAL

Product containers will contain product residue and must be disposed of properly. Label warnings must be observed at all times. All containers must be disposed in accordance with federal, state, and local regulations.

IMPORTANT NOTICE

Always read and acquaint yourself with Tri-Chem's Technical Data Sheet, SDS (safety data sheet), and product labels for each individual product prior to mixing and prior to use. For further assistance, product questions, additional information and/or unexpected or unusual installation conditions—contact your local representative or Tri-Chem directly for recommendations. Kit components are pre-measured for optimal performance. Catalyzation errors due to incorrect mixing in the field voids product warranty.

WARRANTY

Information about Tri-Chem products is given, to the best of our knowledge, based on tests and experience. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you make your own tests to determine suitability of the product for the particular purpose. As products are often applied or used under conditions beyond our control, Tri-Chem cannot guarantee anything except the quality of its products. Tri-Chem warrants that the products meet the specifications set forth by Tri-Chem, but we reserve the right to change any given specification prior to notice. Tri-Chem **DISCLAIMS ALL WARRANTIES RELATING TO THE PRODUCTS AND THEIR APPLICATION, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.** Receipt of a Tri-Chem product constitutes acceptance of the terms of this limited warranty and the terms and conditions set out in our invoice, contrary provisions of buyer's purchase documents notwithstanding. Upon receipt of the merchandise, purchaser has 30 days to notify Tri-Chem, in writing, that materials are defective. In the event Tri-Chem finds that the product delivered is off specification, Tri-Chem will, at its sole discretion, either replace the product(s) or refund the purchase price thereof, and Tri-Chem's choice of one of these remedies is the buyer's sole remedy. In no event shall the liability of Tri-Chem exceed the purchase price of shipped merchandise. Claims must be in writing. Claims after 30 days are void. Tri-Chem will, under no circumstances, be liable for special, incidental, or consequential damages. This warranty supersedes all other guaranties, whether oral or written, and whether expressed, implied, or statutory. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Certain products may contain chemicals that may cause serious physical injury. Before using, please read the Safety Data Sheet and follow all precautions to prevent bodily harm.