



TRI-CHEM

ACROGUARD EDPM Roof Coating

DESCRIPTION

AcroGuard is an elastomeric copolymer liquid rubber coating modified for excellent elongation, tensile strength, UV resistance, and exceptional weathering characteristics. This flexible membrane has excellent waterproofing performance and resistance to ozone as well as low temperature flexibility.

This product has shown good adhesion to many properly prepared substrates including EDPM.

CAUTION

Please refer to the SDS for more detailed precautionary measures, handling instructions, and emergency procedures. **KEEP OUT OF REACH OF CHILDREN.**

HMIS SYMBOL

3	3
3	0
Personal Protection	

Health	3
Fire	3
Reactivity	0
Personal Protection	

FIRST-AID

Eyes: Flush eyes with water for at least fifteen minutes and consult a physician.

Skin: Skin contact will normally cause no more than irritation but wash affected area with soap and water and remove contaminated clothing promptly.

Inhalation: Remove victim to fresh air and administer oxygen if necessary.

Ingestion: Do NOT induce vomiting. Keep person warm and consult a physician immediately.

STORAGE

Store at room temperatures between 60°F and 80°F. Do not allow AcroGuard to freeze. If it does freeze, do not use. An indication that AcroGuard has frozen is a cottage cheese consistency.

DIRECTIONS

- Membrane surface must be clean, dry, and free of foreign material and contaminants prior to the application of AcroGuard.
- Spray apply using a spray head swivel airless spray gun and spray tip. When using a spray applicator, use an air compressor capable of supplying 90-100 psi of air at a rate of 124 cu. ft. per minute.
- Apply AcroGuard in a one-coat application to achieve a coverage rate of approximately 100 sq. ft per gallon.
- If applying by roller method, AcroGuard base coat must be applied prior to rolling on the AcroGuard roof coating.
- Note: Roller application may produce a textured surface appearance