



TRI-CHEM

WHITE ELASTOMERIC ROOF COATING

Reflective Rubber Roof Coating

DESCRIPTION

White Elastomeric Roof Coating is a thick, rubber-like coating that expands and contracts with the roof. The superior reflectivity lowers interior temperatures resulting in energy savings.

FEATURES

- Resists cracking and peeling from severe heat and cold
- Excellent adhesion on metal, aged galvanized and pre-painted metal, urethane and polystyrene, polyester plastic panels, flat and barrel tiles, and some single-ply roofing materials
- Expands and contracts with the roof
- VOC-compliant with the Volatile Organic Compounds limits
- Easily applied with a soft brush, roller, or airless spray.
- Has excellent suspension and requires minimum stirring
- Custom colors available in min of 300 gallons

FIRST-AID

Eyes: Rinse immediately with plenty of water and seek medical attention.

Skin: Wash thoroughly with soap and water. Remove contaminated clothing and shoes and wash before reuse. In the case of skin irritation or allergic reactions see a physician.

Inhalation: Remove victim to fresh air and get medical attention if difficulty breathing.

Ingestion: Do NOT induce vomiting. Get medical attention immediately.

CAUTION

Please refer to the SDS for more detailed precautionary measures, handling instructions, and emergency procedures.
KEEP OUT OF REACH OF CHILDREN.

COVERAGE

Will cover 80 - 100 sq. ft. per gallon at 6 - 8 mils thickness

DIRECTIONS

All surfaces to be coated must be power washed and thoroughly rinsed to allow the coating to adhere to the substrate. **DO NOT THIN.** For best results, apply with a soft brush, roller, or airless spray. Avoid excessive brushing. Apply at temperatures above 50°F. One coat will normally cover any previous coating, but two coats are recommended. If roof is hot, spray with water to prevent the coating from drying too fast. If coating is subjected to rain before it dries and some wash-off occurs, it is essential to wash stained surfaces as soon as possible with warm, soapy water. Dry time between coats is 24 hours at 70°F.

HMIS SYMBOL

Health	2
Fire	2
Reactivity	0
Personal Protection	